



ANALYSIS CERTIFICATE

25 July, 2022

OUR REF:	107772F
TO:	Ardex NZ Ltd
ATTN:	Steven Irvine

SAMPLE OF:	Ardex ST	SAMPLE TYPE:	As received
SAMPLE TYPE:	Neutral Cure, Non-Staining Natural Stone Silicone	DATE RECEIVED:	18/07/2022
SAMPLE DATE:	-	DATE TESTED:	18-20/07/2022
		ORDER NO:	-

SPECIFICATION:	Green Building Council of Australia Green Star Design & As Built V1.3-13.1.1B Green Star Interiors V1.3-12.1.1B
DETAILS:	Max TVOC content in grams per litre (g/L) of ready to use product in the category of 'Architectural sealant, waterproofing sealant' = 250

RESULTS

	Result	Method
Total Non-Volatile Content, %w/w	96.3	Oven-drying @ 110°C (60mins)
Total Water Content, %w/w	<0.1	Karl Fischer titration
Density, g/mL	1.02	Gravimetry
Exempt Compounds	None specified	

	Result	Method
Total Volatile Organic Compounds, g/L	38	SCAQMD METHOD 304-91

Note: Specification was provided by the client. This sample complies with the specification.

Analyst H. Singh

Authorised by [Signature]

This report relates only to the sample provided
This Report Shall Not Be Reproduced Except In Full

MEMBER OF THE NEW ZEALAND ASSOCIATION OF CONSULTING LABORATORIES

37 Spring Street, Freemans Bay, Auckland 1011 - PO Box 437, Shortland Street, Auckland 1140, New Zealand
Phone: (09) 360 2077 - Mobile: 021 145 1567 - Email: office@flinderscook.co.nz

Website: www.flinderscook.co.nz